

**Specific Test List: British Standard BS 5852**

BS 5852:2006 - Methods of Test for Assessment of the Ignitability of Upholstered Seating by Smouldering and Flaming Ignition Sources (Composite Mock-Ups)

Ignition Source	Number of Pieces of Each Product Required	Performance Time
#0: Smouldering Cigarette	3 pieces: 18" x 18" x 3" 3 pieces: 12" x 18" x 3"	7 - 10 days
#1: 20 Seconds, 35 mm Butane Flame	3 pieces: 18" x 18" x 3" 3 pieces: 12" x 18" x 3"	7 - 10 days
#2: 40 seconds, 145 mm Butane Flame	3 pieces: 18" x 18" x 3" 3 pieces: 12" x 18" x 3"	7 - 10 days
#3: 70 seconds, 240 mm Butane Flame	3 pieces: 18" x 18" x 3" 3 pieces: 12" x 18" x 3"	7 - 10 days
#4: 8.5 gram wooden crib	3 pieces: 18" x 18" x 3" 3 pieces: 12" x 18" x 3"	7 - 10 days
#5: 17 gram wooden crib	3 pieces: 18" x 18" x 3" 3 pieces: 12" x 18" x 3"	7 - 10 days
#6: 57 gram wooden crib	3 pieces: 18" x 18" x 3" 3 pieces: 12" x 18" x 3"	7 - 10 days
#7: 126 gram wooden crib	3 pieces: 18" x 18" x 3" 3 pieces: 12" x 18" x 3"	7 - 10 days

**NOTE: BS 5852 provides for the testing of composite mock-ups, which are usually a combination of fabric and filling materials. If individual components are submitted (such as fabric separately; or filling material separately) Govmark will supply a corresponding component to form a composite.**

**The tests contained in this list are not to be considered all-inclusive. Other tests not listed might apply. In order to assure that you are considering the proper test, please contact us or complete a "Request for Quote" form.**